

## ALPHA-SILICON NITRIDE GRADE M 11 HIGHER PURITY COARSE

<b>Chemical Formula</b>	$\alpha\text{-Si}_3\text{N}_4$
<b>Chemical Name</b>	Silicon Nitride
<b>Description of Product</b>	Higher Purity $\text{Si}_3\text{N}_4$
<b>HS Number</b>	28500030
<b>Grades Available</b>	<b>Product Designation</b> $\text{Si}_3\text{N}_4$ Grade M 11 higher purity coarse

---

### Chemical Characteristics

(Mass fraction in % [cg/g]; ppm [ $\mu\text{g/g}$ ])

	Grade M 11 hp coarse		
N	min.	38.0	%
C	max.	0.3	%
O	max.	2.0	%
Al	max.	0.005	%
Ca	max.	0.001	%
Fe	max.	0.001	%
Co	max.	0.005	%
Cr	max.	0.001	%
Cu	max.	0.005	%
K	max.	0.001	%
Mg	max.	0.001	%
Mn	max.	0.001	%
Mo	max.	0.001	%
Na	max.	0.001	%
Ni	max.	0.001	%

### Physical Characteristics

Specific Surface Area <sup>1)</sup>	9.0	- 12.0	m <sup>2</sup> /g
Particle Size Distribution <sup>2)</sup>			
D 90 %	1.5	- 2.5	$\mu\text{m}$
D 50 %	0.7	- 0.9	$\mu\text{m}$
D 10 %	0.2	0.5	$\mu\text{m}$

---

1) TRISTAR by BET (ASTM D 3663), 2) MASTERSIZER by Laser Light Diffraction per ASTM B 822, deagglomeration with high energy ultrasonic before analysis.

<b>Packaging</b>	25 kg steel drums with polyethylene inlet. (60 Liter) 8 drums on one pallet CP1 (1000x1200 mm) = 1 Packaging-unit of 200 kg. Other packaging / quantity on request. <b>Lot Size</b> Höganäs silicon nitride powders are available in homogeneous lots up to 5 tons.
<b>Storage and Handling</b>	Storage and handling are subject to the rules and regulations in the country of use. Store in a closed container.
<b>Hazards identification in Advertising (REGULATION (EC) No 1272/2008)</b>	None.
<b>Documentation</b>	An inspection document in accordance with EN 10204 is supplied with every shipment.

## Höganäs Germany GmbH

Im Schleeke 78-91  
38642 Goslar/Germany

Säckinger Straße 51  
79725 Laufenburg/Germany

Phone +49 5321 751-53753

<https://www.hoganas.com/en/contact/>

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Höganäs Germany GmbH. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases Höganäs Germany GmbH from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Höganäs Germany GmbH. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. In case of order please refer to issue number of the respective product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sale and Delivery.