

TITANIUM CARBIDE STANDARD

Description of Product TiC is used in the production of solid titanium carbide grades of hardmetal and in the manufacture of mixed crystal (triple / tetra carbide) and black ceramics.

Grades Available **Product Designation**
TiC STD 120
TiC STD 250

Chemical Characteristics¹⁾
(Mass fraction in % [cg/g]; ppm [μ g/g])

	TiC STD 120		TiC STD 250	
C_{total}	min.	19.2 %	min.	19.2 %
C_{free}	max.	0.5 %	max.	0.5 %
$C_{combined}$	min.	19.1 %	min.	19.1 %
O	max.	1.3 %	max.	0.8 %
N	max.	0.3 %	max.	0.3 %
Ca	max.	100 ppm	max.	100 ppm
Fe	max.	2500 ppm	max.	2500 ppm
Na	max.	100 ppm	max.	100 ppm
S	max.	100 ppm	max.	100 ppm
Si	max.	150 ppm	max.	150 ppm

Physical Characteristics

Fisher number (as supplied) 1.0 - 1.5 μ m 2.0 - 3.0 μ m

1) Information on chemical analytical methods and list of analyzed items on request.

Packaging Standard Packaging
TiC STD 120: 25 kg in a specially coated 30 l steel drum with a polyethylene bag.
TiC STD 250: 50 kg in a specially coated 30 l steel drum with a polyethylene bag.

Storage and Handling Storage and handling are subject to the rules and regulations in the country of use.

Hazards identification in Advertising (REGULATION (EC) No 1272/2008 Article 48)
None.

Documentation An inspection document in accordance with EN 10204 is supplied with every shipment.

Höganäs Germany GmbH

Im Schleeke 78-91
38642 Goslar/Germany

Säckinger Straße 51
79725 Laufenburg/Germany

Phone +49 5321 751-53753

<https://www.hoganas.com/en/contact/>

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Höganäs Germany GmbH. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases Höganäs Germany GmbH from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Höganäs Germany GmbH. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. In case of order please refer to issue number of the respective product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sale and Delivery