

AMPERIT[®] 161

Chemical Formula	Nb
Chemical Name	Niobium
Grades Available	Product Designation AMPERIT [®] 161.065 30/10 µm

Chemical Characteristics

(Mass fraction in % [cg/g]; ppm [µg/g])

	Limit		
Nb	min.	99.9 %	
C	max.	100	ppm
H	max.	150	ppm
N	max.	150	ppm
O	max.	1000	ppm
Ca	max.	10	ppm
Cr	max.	10	ppm
Fe	max.	100	ppm
K	max.	3	ppm
Mg	max.	300	ppm
Mn	max.	2	ppm
Mo	max.	100	ppm
Na	max.	3	ppm
Ni	max.	10	ppm
Si	max.	50	ppm
Ta	max.	500	ppm
W	max.	100	ppm

Physical Characteristics¹⁾

D 90 %	40	-	46	µm
D 50 %	22	-	28	µm
D 10 %	11	-	17	µm

1) MASTERSIZER by Laser Light Diffraction per ASTM B 822 and ISO 13320 (sample preparation by ultrasonic treatment)

Packaging	Packaging according to the Dangerous Goods / Regulations Class 4.1 "Flammable Solids.
Storage and Handling	Storage and handling are subject to the rules and regulations in the country of use.
Documentation	An inspection document in accordance with EN 10204 is supplied with every shipment.
Remarks	Always mix well before using.
Hazards identification in Advertising (REGULATION (EC) No 1272/2008 Article 48)	Flammable solids Category 1

Höganäs Germany GmbH

Im Schleeke 78-91
38642 Goslar/Germany

Säckinger Straße 51
79725 Laufenburg/Germany

Phone +49 5321 751-53753

<https://www.hoganas.com/en/contact/>

The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Höganäs Germany GmbH. All information is given without warranty or guarantee. It is expressly understood and agreed that the customer assumes and hereby expressly releases Höganäs Germany GmbH from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Höganäs Germany GmbH. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent. In case of order please refer to issue number of the respective product data sheet. All deliveries are based on the latest issue of the product data sheet and the latest version of our General Conditions of Sale and Delivery.