


Höganäs portfolio for **Additive manufacturing**



Every particle counts

Höganäs 
POWDER THAT EMPOWERS®

Co Alloys

Amperprint® 0037 CoCrMo (F 75)								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	27.0	30.0	Ti		0.10
			Mo	5.0	7.0	C		0.02
			Si		1.00	P		0.02
			Mn		1.00	B		0.010
			Fe		0.75	S		0.01
			W		0.20	O		0.05
			Ni		0.10	N		0.25
			Al		0.10	Co Balance		

Ni Alloys

Amperprint® 0233 Haynes®282®								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	18.0	22.0	Si		0.20
			Co	9.0	11.0	P		0.015
			Mo	8.0	9.0	S		0.015
			Ti	1.9	2.3	B		0.010
			Al	1.3	1.7	O		0.030
			C	0.04	0.08	N		0.020
			Fe		1.5			
			Mn		0.30	Ni Balance		



Amperprint® 0211 Ni-SA 230

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	20.0	24.0	Co		3.00
			W	13.0	15.0	Cu		0.20
			Mo	1.0	3.0	Nb		0.20
			Mn	0.30	1.00	Ta		0.20
			Si	0.25	0.75	Ti		0.10
			Al	0.20	0.50	B		0.015
			C	0.05	0.15	P		0.03
			La	0.005	0.050	S		0.010
			Fe		3.000	Ni Balance		

Amperprint® 0221 Ni-SA 247 LC

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	W	9.3	9.7	Fe		0.20
			Co	9.0	9.5	Cu		0.10
			Cr	8.0	8.5	Mn		0.10
			Al	5.3	5.8	Si		0.20
			Ta	3.0	3.4	P		0.015
			Hf	1.2	1.6	S		0.010
			Ti	0.6	0.9	H		0.005
			Mo	0.4	0.6	O		0.020
			C	0.05	0.1	N		0.020
			B	0.01	0.02			
			Zr	0.005	0.020	Ni Balance		

Amperprint® 0153 Ni-SA 625 (Inconel® 625, 2.4856)

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	20.0	23.0	Mn		0.10
			Mo	8.0	10.0	C		0.05
			Nb	3.15	4.15	Ta		0.05
			Fe		2.5	P		0.030
			Co		1.00	S		0.015
			Si		0.50	B		0.010
			Cu		0.50	O		0.025
			Ti		0.40	N		0.025
			Al		0.40	Ni Balance		

Amperprint® 0181 Ni-SA 718 (Inconel® 718, 2.4668)

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Ni	50.0	55.0	Mn		0.35
			Cr	17.0	21.0	Cu		0.30
			Nb	4.75	5.50	Ta		0.05
			Mo	2.8	3.3	P		0.015
			Ti	0.6	1.2	S		0.015
			Al	0.2	0.8	B		0.006
			C	0.02	0.08	O		0.030
			Co		1.0	N		0.025
			Si		0.35	Fe Balance		

Amperprint® 0151 Ni-SA 738 LC								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	15.7	16.3	B	0.007	0.012
			Co	8.0	9.0	Fe		0.50
			Al	3.2	3.7	Mn		0.20
			Ti	3.2	3.7	Si		0.10
			W	2.4	2.8	S		0.015
			Mo	1.5	2.0	P		0.015
			Ta	1.5	2.0	O		0.030
			Nb	0.6	1.10	N		0.020
			C	0.06	0.13			
			Zr	0.015	0.08	Ni Balance		

Amperprint® 0152 Ni-SA 939								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	21.0	23.0	Si		0.20
			Co	18.0	20.0	Zr		0.100
			Ti	3.0	4.5	P		0.030
			W	1.0	3.0	B		0.01
			Al	1.5	2.5	S		0.010
			Ta	1.0	2.0	Bi		0.0020
			Nb	0.5	1.5	Pb		0.0010
			C		0.25	Cd		0.0005
			Mn		0.20	Ni Balance		

Amperprint® 0228 NiCrFeMo (HX 2.4665)								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	20.5	23.0	Al		0.50
			Fe	17.0	20.0	Ti		0.50
			Mo	8.0	10.0	S		0.015
			Co	0.5	2.5	P		0.015
			W	0.2	1.0	B		0.009
			C	0.05	0.10	O		0.030
			Si		1.0	N		0.020
			Mn		1.0	Ni Balance		

Fe Alloys

Amperprint® 1556 FeNiCoMo (18Ni30, 1.2709)								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Ni	17.0	19.0	C		0.03
			Co	8.5	10.0	P		0.010
			Mo	4.50	5.20	S		0.010
			Ti	0.50	1.00	O		0.035
			Al	0.05	0.15	N		0.02
			Mn		0.15			
			Si		0.10	Fe Balance		

Amperprint® 0638 FeCrMoSiVMn (1.2343)								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	4.80	5.50	C	0.33	0.41
			Mo	1.10	1.50	Mn	0.25	0.50
			Si	0.80	1.20	P		0.030
			V	0.30	0.50	S		0.020
						Fe Balance		

Amperprint® 0634 FeCrMoSiVMn (1.2344)								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	4.80	5.50	C	0.35	0.42
			Mo	1.20	1.50	Mn	0.25	0.50
			Si	0.80	1.20	P		0.030
			V	0.85	1.15	S		0.020
						Fe Balance		

Amperprint® 0717 316L, 1.4404								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	16.5	18.5	P		0.045
			Ni	10.0	14.0	S		0.015
			Mo	2.0	3.0	O		0.05
			Mn	0.15	2.0	N		0.03
			Si		1.0			
			C		0.03	Fe Balance		

Amperprint® 0742 15-5 PH, 1.4540								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	14.0	15.5	C		0.07
			Ni	3.50	5.50	P		0.04
			Cu	2.50	4.50	S		0.03
			Nb	0.15	0.45	O		0.06
			Mn		1.00	N		0.03
			Si		1.00	Fe Balance		

Amperprint® 0711 17-4 PH, 1.4542								
Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	15.0	17.5	C		0.07
			Ni	3.00	5.00	P		0.040
			Cu	3.00	5.00	S		0.030
			Nb+Ta	0.15	0.45	O		0.06
			Mn		1.00	N		0.02
			Si		1.00	Fe Balance		

Höganäs – AM

AM 316L 1.4404

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	16,0	18,0	C		0,030
			Ni	11,0	14,0	Si	0,5	1,0
			Mo	2,0	3,0	Mn	1,0	2,0
						Fe Balance		

AM 420 420A, 1.4021

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	12,0	13,5	Si	0,4	0,6
			Mn	1,0	1,4	C	0,2	0,25
						Fe Balance		

AM H13 1.2344

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	4,75	5,50	Mn	0,2	0,4
			Mo	1,25	1,75	Si	0,8	1,2
			V	0,80	1,20	C	0,30	0,40
						Fe Balance		

AM 4130 1.7218, 25CrMo4


Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	0,7	1,2	C	0,27	0,34
			Mn	0,3	0,7	P		0,035
			Mo	0,1	0,4	S		0,040
			Si	0,2	0,5			
						Fe Balance		

AM 4140
1,7225, 42CrMo4

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	0,7	1,2	C	0,37	0,44
			Mn	0,7	1,1	P		0,035
			Mo	0,1	0,4	S		0,040
			Si	0,2	0,5			
						Fe Balance		

AM 16MnCr5
1.7131

Process			Chemical Composition (wt %)					
Selective Laser Melting	Electron Beam Melting	Laser Metal Deposition	Element	Min	Max	Element	Min	Max
✓	✓	✓	Cr	0,75	1,15	C	0,13	0,20
			Mn	0,95	1,35	P		0,035
			Si	0,2	0,5	S		0,040
						Fe Balance		





Driving positive change through material innovation

Höganäs' vision is to drive positive change through material innovation, which in turn will help us in our ambition to become the globally preferred partner for sustainable powder materials. Powder technology provides endless opportunities; not only does it empower our customers to reduce their material and energy consumption, but it also helps them use new and better techniques that make final products more efficient and less expensive. In short, powders are a resource-efficient alternative that are optimal for a range of industries.

World leader in powders

Höganäs is a global company with local presents all over the world. We are a global leader in advanced ceramic and metal powders. Contact your nearest Höganäs office today, click or scan the QR-code:



***Find your metal powder for 3D printing
with PowderFinder, please scan the
QR code.***

www.hoganas.com/am

Höganäs 
POWDER THAT EMPOWERS®